

A Novel Dressing for Wound Care Based on Konjac Glucomannan

¹Sugeng Mashudi, ²T.N. Saifullah, ³Lukman Handoko. ⁴Rochmad Aldi Purnomo

^{1,4}Universitas Muhamamdiyah Ponorogo, Indonesia

²Universitas Gadjah Mada Yogyakarta, Indonesia

³Politeknik Perkapalan Negeri Surabaya

Email: sugengmashudi@umpo.ac.id

Abstract

Wound management has become a crucial component of healthcare systems since wound healing continues to be a problem for the nursing sciences. One area that could provide novel methods for regenerative complementary nursing is konjac glucomannan. It is necessary to emphasize the significance when konjac glucomannan is incorporated into biomaterials, it may induce particular qualities that make the biomaterials more effective. They are appealing as wound dressing materials. In this review, we will talk about the first line of bioactive konjac glucomannan-based dressings that are often used in nursing practice. These include semi-permeable films, hydrogel dressings, hydrocolloid dressings, alginate dressings, non-adherent contact layer dressings, and multilayer dressings. This review will also point out that there isn't enough high-quality evidence and that more advanced trials need to be done because most current wound healing treatments don't work well, either structurally or functionally. Konjac glucomannan is a unique tool that can be used to help heal wounds. They can be made to closely resemble the natural processes that lead to tissue repair.

Keywords: wound dressings, konjac glucomannan, complementary nursing, hydrogel dressings, hydrocolloid dressings, tissue repair, nursing sciences.

Introduction

In order for a wound to heal, it goes through four stages: hemostasis, inflammation, proliferation, and remodelling (Stoica et al., 2020). Healing a wound is a very complicated process that takes a long time to finish (Castaño et al., 2018). The remodelling phase, which creates the right environment for healing, can last from 21 days to a year (Tamahkar et al., 2020).

Care for patients with wounds requires a wide variety of clinical measurements, procedures, and treatments that make up the whole spectrum of wound management. Managing wounds properly is a major clinical difficulty, and there is a growing need in this area of medicine. Researchers are focusing on improving chronic wound care by creating novel and effective wound dressing materials. In terms of how physicians decide which dressing product to use, it's crucial that they first examine the patient's pain and the wound's underlying cause. Wound treatment techniques that take use of dressing characteristics to promote healthy innate responses should be adopted wherever possible.

It is essential that the wound's depth, nature, and exudates all be taken into account while selecting a dressing. If a wound dressing can't keep the area it's covering wet, it won't be able to do its job properly and healing won't be able to proceed. The dressing should also allow for adequate gas permeability (İnal & Mülazımoğlu, 2019), absorb excess exudate from the wound surface, and keep the wound moist. Another crucial feature is its antibacterial medium, which acts as a physical barrier to microorganisms (Tao et al., 2019). The dressing must be biocompatible, inexpensive, and simple to apply without needing regular renewal (Bechstein, 2018; Tamahkar et al., 2020).

This study discusses the physical and biological features, forms, benefits, drawbacks, and indications and contraindications of the first-line bioactive dressing class based on konjac glucomannan used in nursing practice. Konjac glucomannan are used in hydrogels and hydrocolloids wound dressings. This study also highlights the absence of high-quality data and the need for future improved designed studies since present wound healing treatments seldom provide good structural or functional results. Hydrocolloids, hydrogels, fiber mats, and others have been made from natural and manmade materials. Konjac glucomannan-based therapies may transport several nursing care to the target location and target the intricacy of the natural wound-healing process, opening up new possibilities in wound care.

Hydrogel Dressings

Wound healing is a complicated, dynamic process that creates a distinct wound microenvironment. To improve healing efficiency, multifunctional skin replacements should be developed (Qu et al., 2019). Softness and water retention are advantages of hydrogels (Mir et al., 2018). Hydrogels minimize tissue dehydration, making them suitable for treating acute/chronic wounds, burns, and diabetic foot ulcers. Hydrogels are insoluble, swellable polymers with a high water content that produce amorphous gels or elastic solid sheets or films. Rehydrating necrosis and slough with these dressings helps autolytic debridement. Hydrogels are semitransparent and semipermeable [63]. Hydrogels, non-adherent dressings, accelerate wound healing and reduce discomfort by up to 5 °C. Hydrogel dressings enhance wound re-epithelialization without residues. Hydrogel requires a secondary dressing, yet it still provides water to the wound bed. The flexible hydrogel sheets might be trimmed to suit the wound. Hydrogel dressings are best for dry, little exuding wounds due to their high water content (70–90%). Fluid buildup may cause skin maceration and bacterial growth. It stinks and infects wounds. Hydrogels are also fragile. Hydrogels should be replaced 1–3 days depending on wound hydration to avoid skin maceration, dressings must be changed often (Li et al., 2015).

Konjac glucomannan were added to hydrogel dressings to promote healing and antibacterial activity. Developed biocompatible chitosan and poly(vinyl alcohol) hydrogels with embedded silver nanoparticles as an effective antibacterial agent to create wound dressing materials with improved characteristics. Hydrogel dressings were non-cytotoxic and effective against *S. aureus* and *E. coli*. Because the basic therapy for chronic wounds is to avoid infection while the wound heals, pressure ulcers are particularly difficult (Nunes et al., 2011). The silver nanoparticles-

based PVP/alginate/chitosan hydrogel in the ratio 10:1.2:1.8 has antibacterial capabilities, minimal cytotoxicity, decreased cost (compared to commercial ones like Algivon®, ACTICOATTM, and Suprasorb® A + Ag), and maximal swelling.



Sources: (Wang et al., 2021)

Figure 1. Potency of herbal medicine hydrogel dressing based on konjac glucomannan

Liposomal hydrogel wound dressing reduces bacterial contamination and infection spread. Nunes et al. showed that collagen-based films with liposome-loaded usnic acid improve burn healing. Created and tested a mupirocin liposomal hydrogel for diabetic wounds (Tsioli et al., 2018). They showed that this dressing combines prolonged medication release to prevent infection and moist wound dressing with efficient fluid absorption. Created a chitosan gel formulation with liposomes carrying epidermal growth factor to test its effects on rat second-degree burn wound healing. Cell proliferation and epithelisation increased histochemically.

Monjac glucomann has various benefits, in addition to lowering cholesterol levels (sugeng mashudi et al., 2022), it can also be used in wound care. Hydrogels provide a moist, cold environment for wound healing, promote high water vapor permeability, and prevent microorganisms from entering the wound.

Hydrocolloid Dressing

Colloidal, gel-forming materials, elastomers, and adhesives make hydrocolloid dressings (Kong et al., 2020). Hydrocolloid sheets have two layers. The inner layer is a self-adhesive hydrophilic polymer matrix containing scattered gelatin, pectin, and other compounds (Enescu et al., 2020). The outer polyurethane layer shields the wound from pathogens, foreign debris, and shear

stresses. CMC, gelatin, and pectin are hydrocolloid dressings. Thin films, sheets, or composite dressings are used for mild to moderately leaking wounds (Aruan et al., 2017). Powders and pastes include hydrocolloid dressings (Matsuzaki et al., 2018). Gel formation alters physical state after exudate absorption. The painless dressing removal and ability to treat acute and chronic wounds in children are the most essential features (Derwin R & Webster, 2018). That may be why hydrocolloid dressings are the most popular (Matsuzaki et al., 2018). Hydrocolloid wound dressings, made from a hydrophobic pressure sensitive adhesive (continuous phase) and hydrophilic filler (dispersed phase), heal wounds quicker with less discomfort (Boyko et al., 2018). Patients may do daily activities without wound harm (Moore & Webster, 2018).

Hydrocolloid dressings are semi-permeable to water and gas vapors but not fluids or microorganisms. Infected wounds require oxygen to heal, but these coverings usually prevent water vapor exchange (Aruan et al., 2017). Hydrocolloids are waterproof and cushioning, making them useful (Janowska et al., 2018). Hydrocolloid dressings should be replaced daily until drainage appears underneath them, then every three days to once a week (Chamorro et al., 2019).

Pressure ulcer therapy often uses hydrocolloids (Halim et al., 2018). Hydrocolloid dressings outperform gauze dressings due to the frequency of healed wounds and reduced pressure ulcer dimensions (Ma et al., 2019). In 2018, (Chou et al., 2020) found that chitosan derivative film is comparable to hydrocolloid dressing for superficial and abrasion wounds. Hydrocolloid dressing was tested for neurosurgical wounds according to current wound healing (Clark, 2018). Clinical wound infection, healing, and cost-effectiveness assessments showed outstanding wound healing and aesthetic benefits.



Sources: (Cuschieri et al., 2013)

Figure 2. Hydrocolloid applied to entire wound bed and monitored closely (clinic visits

every other day) for signs of deterioration and infection: week 3

Hydrocolloid dressings based on Nanotechnology might support all wound healing stages in the future. owing to a paucity of publications.

Conclusions

Wound treatment is crucial and growing globally. Evidence-based Nursing wound care requires knowledge of wound dressing products and clinical competence in dressing selection. Differentiating wound-healing from conventional materials treatment may help treat chronic and ischemic ulcers by herbal materials. Preclinical research is necessary, specifically from konjac glucomannan for diabetes foot ulcer. Research is required. to find novel konjac glucomannan material that accelerate chronic wound healing healing. New biocompatible konjac glucomannan that can controlling all wound healing stages, including antimicrobial, self-healing, good mechanical characteristics and wound dressing adherence to increase performance. This study may lead to clinical applications.

Acknowledgments: This work was supported by a grant from KEDAIREKA platform from KEMDIKBUDRISTEKDIKTI.

Conflicts of Interest: The authors declare no conflict of interest.

References

- Aruan, N. M., Sriyanti, I., Edikresnha, D., Suciati, T., Munir, M. M., & Khairurrijal. (2017). Polyvinyl Alcohol/Soursop Leaves Extract Composite Nanofibers Synthesized Using Electrospinning Technique and their Potential as Antibacterial Wound Dressing. *Procedia Engineering*, 170, 31–35. <https://doi.org/https://doi.org/10.1016/j.proeng.2017.03.006>
- Bechstein, W. O. (2018). Towards Simpler and Reliable Wound Care. In *Deutsches Arzteblatt international* (Vol. 115, Issue 13, pp. 211–212). <https://doi.org/10.3238/arztebl.2018.0211>
- Boyko, T. V, Longaker, M. T., & Yang, G. P. (2018). Review of the Current Management of Pressure Ulcers. *Advances in Wound Care*, 7(2), 57–67. <https://doi.org/10.1089/wound.2016.0697>
- Castaño, O., Pérez-Amodio, S., Navarro-Requena, C., Mateos-Timoneda, M. Á., & Engel, E. (2018). Instructive microenvironments in skin wound healing: Biomaterials as signal releasing platforms. *Advanced Drug Delivery Reviews*, 129, 95–117. <https://doi.org/10.1016/j.addr.2018.03.012>
- Chamorro, A. M., Vidal Thomas, M. C., Mieras, A. S., Leiva, A., Martínez, M. P., & Hernández Yeste, M. M. S. (2019). Multicenter randomized controlled trial comparing the effectiveness and safety of hydrocellular and hydrocolloid dressings for treatment of category II pressure ulcers in patients at primary and long-term care institutions. *International Journal of Nursing Studies*, 94, 179–185. <https://doi.org/10.1016/j.ijnurstu.2019.03.021>
- Chou, H.-Y., Weng, C.-C., Lai, J.-Y., Lin, S.-Y., & Tsai, H.-C. (2020). Design of an Interpenetrating Polymeric Network Hydrogel Made of Calcium-Alginate from a Thermos-

- Sensitive Pluronic Template as a Thermal-Ionic Reversible Wound Dressing. *Polymers*, 12(9). <https://doi.org/10.3390/polym12092138>
- Clark, M. (2018). Alginates in Dressings and Wound Management. In B. H. A. Rehm & M. F. Moradali (Eds.), *Alginates and Their Biomedical Applications* (pp. 213–222). Springer Singapore. https://doi.org/10.1007/978-981-10-6910-9_8
- Cuschieri, L., Debosz, J., Miiller, P., & Celis, M. (2013). Autolytic debridement of a large, necrotic, fully occluded foot ulcer using a hydrocolloid dressing in a diabetic patient. *Advances in Skin and Wound Care*, 26(7), 300–304. <https://doi.org/10.1097/01.ASW.0000429779.48138.c0>
- Derwin R, M. Z. E. H., & Webster, J. (2018). Hydrocolloid dressings for donor sites of split thickness skin grafts. *Cochrane Database of Systematic Reviews*, 1. <https://doi.org/10.1002/14651858.CD012634.pub2>
- Enescu, D. M., Stoicescu, S., Tomiță, M., Nacea, I., Ioniță, D., & Tatar, R. (2020). Management of lower extremity traumatic injuries with negative pressure wound therapy: Experience of a pediatric plastic surgery department. *Injury*, 51 Suppl 4, S9–S15. <https://doi.org/10.1016/j.injury.2020.03.027>
- Halim, A. S., Nor, F. M., Mat Saad, A. Z., Mohd Nasir, N. A., Norsa'adah, B., & Ujang, Z. (2018). Efficacy of chitosan derivative films versus hydrocolloid dressing on superficial wounds. *Journal of Taibah University Medical Sciences*, 13(6), 512–520. <https://doi.org/10.1016/j.jtumed.2018.10.004>
- İnal, M., & Mülazımoğlu, G. (2019). Production and characterization of bactericidal wound dressing material based on gelatin nanofiber. *International Journal of Biological Macromolecules*, 137, 392–404. <https://doi.org/10.1016/j.ijbiomac.2019.06.119>
- Janowska, A., Macchia, M., & Paggi, B. (2018). Advanced Dressings in Pressure Ulcers. In M. Romanelli, M. Clark, A. Gefen, & G. Ciprandi (Eds.), *Science and Practice of Pressure Ulcer Management* (pp. 159–173). Springer London. https://doi.org/10.1007/978-1-4471-7413-4_12
- Kong, D., Zhang, Q., You, J., Cheng, Y., Hong, C., Chen, Z., Jiang, T., & Hao, T. (2020). Adhesion loss mechanism based on carboxymethyl cellulose-filled hydrocolloid dressings in physiological wounds environment. *Carbohydrate Polymers*, 235, 115953. <https://doi.org/10.1016/j.carbpol.2020.115953>
- Li, X., Xu, G., & Chen, J. (2015). Tissue engineered skin for diabetic foot ulcers: A meta-analysis. *International Journal of Clinical and Experimental Medicine*, 8(10), 18191–18196.
- Ma, R., Wang, Y., Qi, H., Shi, C., Wei, G., Xiao, L., Huang, Z., Liu, S., Yu, H., Teng, C., Liu, H., Murugadoss, V., Zhang, J., Wang, Y., & Guo, Z. (2019). Nanocomposite sponges of sodium alginate/graphene oxide/polyvinyl alcohol as potential wound dressing: In vitro and in vivo evaluation. *Composites Part B: Engineering*, 167, 396–405. <https://doi.org/https://doi.org/10.1016/j.compositesb.2019.03.006>
- Matsuzaki, K., Yokono, C., Nomura, Y., & Toriumi, M. (2018). Wound dressings for diabetic

- foot ulcers. *Japanese Journal of Plastic Surgery*, 61(8), 958–970.
<https://doi.org/10.1007/978-3-319-89869-8>
- Mir, M., Ali, M. N., Barakullah, A., Gulzar, A., Arshad, M., Fatima, S., & Asad, M. (2018). Synthetic polymeric biomaterials for wound healing: a review. *Progress in Biomaterials*, 7(1), 1–21. <https://doi.org/10.1007/s40204-018-0083-4>
- Moore, Z. E. H., & Webster, J. (2018). Dressings and topical agents for preventing pressure ulcers. *Cochrane Database of Systematic Reviews*, 2018(12).
<https://doi.org/10.1002/14651858.CD009362.pub3>
- Nunes, P. S., Albuquerque, R. L. C. J., Cavalcante, D. R. R., Dantas, M. D. M., Cardoso, J. C., Bezerra, M. S., Souza, J. C. C., Serafini, M. R., Quitans, L. J. J., Bonjardim, L. R., & Araújo, A. A. S. (2011). Collagen-based films containing liposome-loaded usnic acid as dressing for dermal burn healing. *Journal of Biomedicine & Biotechnology*, 2011, 761593.
<https://doi.org/10.1155/2011/761593>
- Qu, J., Zhao, X., Liang, Y., Xu, Y., Ma, P. X., & Guo, B. (2019). Degradable conductive injectable hydrogels as novel antibacterial. *Chemical Engineering Journal*, 362, 548–560.
<https://doi.org/https://doi.org/10.1016/j.cej.2019.01.028>
- Stoica, A. E., Chircov, C., & Grumezescu, A. M. (2020). Nanomaterials for Wound Dressings: An Up-to-Date Overview. *Molecules*, 25, 2699.
- sugeng mashudi, Dhianita, Aziz, & Syafira. (2022). Effects of Konjac Glucomannan on Blood Profile in Schizophrenia with Hyperglycemia: Pra Eksperimental Study. *International Journal of Public Health*, 1(6).
- Tamahkar, E., Özkahraman, B., Süloğlu, A. K., İdil, N., & Perçin, I. (2020). A novel multilayer hydrogel wound dressing for antibiotic release. *Journal of Drug Delivery Science and Technology*, 58, 101536. <https://doi.org/https://doi.org/10.1016/j.jddst.2020.101536>
- Tao, G., Wang, Y., Cai, R., Chang, H., Song, K., Zuo, H., Zhao, P., Xia, Q., & He, H. (2019). Design and performance of sericin/poly(vinyl alcohol) hydrogel as a drug delivery carrier for potential wound dressing application. *Materials Science & Engineering. C, Materials for Biological Applications*, 101, 341–351. <https://doi.org/10.1016/j.msec.2019.03.111>
- Tsioli, V., Gouletsou, P. G., Galatos, A. D., Psalla, D., Lymperis, A., Sideri, A. I., & Papazoglou, L. G. (2018). The Effect of a Hydrocolloid Dressing on Second Intention Wound Healing in Cats. *Journal of the American Animal Hospital Association*, 54(3), 125–131.
<https://doi.org/10.5326/JAAHA-MS-6604>
- Wang, H., Xu, Z., Zhao, M., Liu, G., & Wu, J. (2021). Advances of hydrogel dressings in diabetic wounds. *Biomater. Sci.*, 9(5), 1530–1546. <https://doi.org/10.1039/D0BM01747G>