





LAMPIRAN



HDPE 45%, Serbuk Kaca 45%, Polimer 10%.





HDPE 50%, Serbuk Kaca 40%, Polimer 10%.



HDPE 60%, Serbuk Kaca 30%, Polimer 10%.



HDPE 65%, Serbuk Kaca 25%, Polimer 10%.



Tabel hasil uji Tarik

No	HDPE	SERBUK KACA	POLIMER	TEBAL (mm)	Lo (mm)	Beban Max (N)
1				3,2	60,8	124,2
2	45%	45%	10%	3,2	60,8	222,1
Rata - Rata						173,1
1				3,2	60,8	222,6
2	50%	40%	10%	3,2	60,8	141,8
Rata - Rata						182,2
1				3,2	60,8	348,8
2	60%	30%	10%	3,2	60,8	117,2
Rata - Rata						233
1				3,2	60,8	164,9
2	65%	25%	10%	3,2	60,8	384,9
Rata - Rata						274,9

Foto-Foto Pembuatan Dan Pengujian Spesimen





